

Test results of PP R60

Description	Standard	Condition	Result	Unit
Tensile strength @Yield	ISO 527	Speed 50 mm/min Gauge Length 50	22.38	Mpa
Elongatin @ Break	ISO 527	Speed 50 mm/min Gauge Length 50	201.44	%
Tensile strength @ Break	ISO 527	Speed 50 mm/min Gauge Length 50	17.66	Mpa
MFI	ASTM D1238	2.16 kg / 230 °C	1	g/10 min
Izod Impact	ISO 180	2.71J/notched/23°C	10.59	kJ/m ²
DSC	ISO 11357/6	10 °C/min N2 50ml/min	Click here	°c
Density	ASTM D792	23°C	0.93	gr/cm ³



- The uncertainty of the test result is based on confidence range of %95 and K=2 which is calculated and Announced due to the customers' demands.

 Info@exirpolymer.com

 +98 31 4564 3030

 +98 912 962 3265

 Exirpolymer.com

 Fa.Exirpolymer.com

 Ar.Exirpolymer.com