

## Recycled Acrylonitrile Butadiene Styrene

Recycled ABS 6800 injection-grade granules have good machinability, chemical resistance, impact strength, dimensional stability, and surface hardness. They are easy to mold and color, suitable for both small and large parts, and have a consistent gray color and uniform quality.

### Technical Properties

Property	Standard	Condition	Result	Unit
<b>MFI</b>	ASTMD1238	10.00 kg / 220 °C	<b>11</b>	g/10 min
<b>Filler Content</b>	ISO3451/1	600°C/30 min	<b>&lt; 5</b>	%
<b>Density</b>	ISO 1183	23°C, 50% RH	<b>1.1</b>	gr/cm <sup>3</sup>
<b>Izod Impact</b>	ISO 180	5.50J/notched/23°C	<b>5</b>	Kj/m <sup>2</sup>
<b>Tensile strength @Yield</b>	ISO 527	Speed 5 mm/Grip 115 mm	<b>37</b>	Mpa
<b>Elongatin @ Yield</b>	ISO 527	Speed 5mm/min GRIP 115 mm	<b>3</b>	%
<b>Tensile strength @ Break</b>	ISO 527	Speed 5mm/min GRIP 115 mm	<b>32</b>	Mpa
<b>Elongatin @ Break</b>	ISO 527	Speed 5mm/min GRIP 115 mm	<b>3</b>	%
<b>Flexural Modulus</b>	ASTMD790	Speed: 1.3mm/min Deflection: 0.5mm	<b>2000</b>	Mpa
<b>Flexural strength</b>	ASTMD790	Speed: 1.3mm/min Deflection: 5.0mm	<b>65</b>	Mpa
<b>DSC</b>	ISO 11357/6	10 °C/min N2 50ml/min	<a href="#">Click</a>	°c

- The uncertainty of the test result is based on confidence range of %95 and K=2 which is calculated and Announced due to the customers' demands.

### Commercial Properties

Property	Value	Property	Value
<b>HS Code</b>	390330	<b>Delivery Terms</b>	CFR, CPT, FCA, FOB
<b>MOQ</b>	1000	<b>Packaging</b>	25 kg Bag – 1000 kg Jumbo Bag
<b>ETD</b>	Negotiable	<b>Payment Terms</b>	Negotiable
<b>MSDS</b>	Yes	<b>Marks &amp; Nos</b>	Negotiable
<b>Product Process</b>	Injection	<b>Color</b>	Gray

## Shipping and Storage Conditions

Away from moisture, sunlight, sharp objects, fire and flame.

### Needs:

[LOI \(Letter of Intent\)](#)

### Other Documents:

You may also need the following documents. Click to download them:

1. [FCO \(Full Corporate Offer\)](#)
2. [PI \(Proforma Invoice\)](#)
3. [CI \(Commercial Invoice\)](#)
4. [PL \(Packing List\)](#)
5. [MSDS \(Material Safety Data Sheet\)](#)

### Quick Access:

- [Visit Our Website](#)
- [Explore Wide Our Range of Recycled Plastic Granules](#)
- [Other Datasheets](#)
- [Loading Capacity Table](#)
- [Suggested Guidelines](#)

#### Technical Consulting

Technical and engineering consulting to find the right product for the customer

[CONTACT NOW](#)

#### Business Consulting

Business consulting in the field of shipping, customs and logistics

[CONTACT NOW](#)

## Contact Information



[info@exirpolymer.com](mailto:info@exirpolymer.com)



+98 912 962 3245



Central office and factory:

Arad Exir Polymer Company, Kaveh 4th St, Kaveh St, Morcheh Khort Industrial Town, Isfahan, Iran